

DATA SHEET - REVIVE PURE WHITE GLOSS

Description	Standard	Unit	Target values								
			115	130	135	150	170	200	250	300	350
Basis weight		GSM	115	130	135	150	170	200	250	300	350
Thickness	ISO 534	µm	81	91	95	105	120	143	184	223	272
Bulk	ISO 534	cm ³ /g	0,70	0,71	0,72	0,72	0,72	0,73	0,75	0,77	0,81
Dynamic Stiffness MD	ISO 5629	mN.m	0,31	0,45	0,50	0,75	1,10	1,80	3,70	6,60	10,80
Dynamic Stiffness CD	ISO 5629	mN.m	0,24	0,35	0,37	0,50	0,78	1,20	2,60	4,30	7,20
CIE Whiteness	ISO 11475	%	124	124	124	124	124	124	124	124	124
Opacity	ISO 2471	%	94,6	95,3	95,4	96,9	98,0	99,1	99,9	100	100
Gloss 75°	ISO 8254-2	%	74	74	74	74	74	74	74	74	74

le 03-02-09



Recycled
Supporting responsible use
of forest resources
Contribue à l'utilisation responsable
des ressources forestières
www.fsc.org Cert no. SGS-COC-003161
© 1996 Forest Stewardship Council



DATA SHEET - REVIVE PURE WHITE SILK

Description	Standard	Unit	Target values								
			115	130	135	150	170	200	250	300	350
Basis weight		GSM	115	130	135	150	170	200	250	300	350
Thickness	ISO 534	µm	92	106	110	122	142	169	227	279	335
Bulk	ISO 534	cm ³ /g	0,80	0,82	0,83	0,84	0,86	0,87	0,93	0,96	0,99
Dynamic Stiffness MD	ISO 5629	mN.m	0,45	0,65	0,70	1,05	1,60	2,40	6,00	11,00	18,00
Dynamic Stiffness CD	ISO 5629	mN.m	0,30	0,45	0,50	0,70	1,10	1,50	4,00	7,00	12,00
CIE Whiteness	ISO 11475	%	124	124	124	124	124	124	124	124	124
Opacity	ISO 2471	%	95,5	96,3	96,5	97,6	98,5	99,4	100	100	100
Gloss 75°	ISO 8254-2	%	32	32	32	32	32	32	32	32	32

le 03-02-09



Recycled
Supporting responsible use
of forest resources
Contribue à l'utilisation responsable
des ressources forestières
www.fsc.org Cert no. SGS-COC-003161
© 1996 Forest Stewardship Council

